

PTO-100
(REV 11-98)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371**

Docket No.: 4296/PCT

U.S. APPLICATION NO. (if known see 37 CFR 1.51)
(not known to be assigned)
107-019416

INTERNATIONAL APPLICATION NO.
PCT/JP00/04435

INTERNATIONAL FILING DATE
03. July, 2000 (03.07.00)

PRIORITY DATE CLAIMED
09. July, 1999 (09.07.99)

TITLE OF INVENTION Aluminum Alloy, Aluminum Alloy Foil, Container and Method of
Preparing Aluminum Alloy Foil

APPLICANT(S) FOR DO/EO/US

Akinori RO; Masaaki ABE; Yoshiki HASHIZUME

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371
3. ☒ This express request to begin national examination procedures (35 U.S.C. 371(f) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1)
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2))
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau)
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired
 - d. ☒ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98, Form PTO-1449, 3 references.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☐ A **FIRST** preliminary amendment.
☐ A **SECOND** or **SUBSEQUENT** preliminary amendment
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☒ Other items or information:
 - a. a Return Receipt Postcard;
 - b. Form PTO-2038 (Credit Card Payment Form);
 - c. 2 Figs. on 2 sheets of formal drawings;
 - d. a copy of International Search Report with English Version.

NOTE: The application has been assigned to TOYO ALUMINIUM KABUSHIKI KAISHA of 6-8, Kyutaro-machi 3-chome, Chuo-ku, Osaka-shi, Osaka, Japan. The Assignment is being submitted herewith for Recordal.

NOTE: The priority of Japanese Patent Application No. 11-195772 filed in Japan on July 9, 1999 is claimed under 35 U.S.C. §119.

USPS EXPRESS MAIL
EL 871 050 090 US
DECEMBER 21 2001

ATTORNEYS DOCKET NUMBER
4296/PCT

CALCULATIONS PTO USE ONLY

Neither international preliminary examination fee (37 CFR 1.482)
nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO
and International Search Report not prepared by the EPO or JPO ~~\$920.00~~

International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO.....	\$890.00 \$840.00
---	---------------------------------

International preliminary examination fee (37 CFR 1.482) not paid to USPTO but
international search fee (37 CFR 1.445(a)(2)) paid to USPTO ~~\$768.00~~

International preliminary examination fee paid to USPTO (37 CFR 1.482)
but all claims did not satisfy provisions of PCT Article 33(1)-(4) **\$670.00**

International preliminary examination fee paid to USPTO (37 CFR 1.482)
and all claims satisfied provisions of PCT Article 33(1)-(4) **US\$5.00**

ENTER APPROPRIATE BASIC FEE AMOUNT =

\$ 890.00

Surcharge of **\$130.00** for furnishing the oath or declaration later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(e)).

S O

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE
Total claims	10 - 20 =	0	X \$18.00

0.5

Independent claims	3	- 3 =	0	X \$78.00
--------------------	---	-------	---	-----------

S O

MULTIPLE DEPENDENT CLAIM(S) (if applicable)

+ \$260.00

§ 0

TOTAL OF ABOVE CALCULATIONS =

\$ 890.00

Reduction of 1/2 for filing by small entity, if applicable. A Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28).

§ 0

SUBTOTAL =

S

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(f)). ☐ +

§ 0

TOTAL NATIONAL FEE =

\$890.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property

\$ 40.00

TOTAL FEES ENCLOSED =

\$ 930.00

Amount to be:

refunded

charged

a. ☒ Form PTO-2038 (Credit Card Payment Form)
~~XXXX~~ in the amount of \$ 930.00 to cover the above fees is enclosed.

b. ☐ Please charge my Deposit Account No. _____ in the amount of \$_____ to cover the above fees.
A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge deficiency in or any/ additional fees which may be required, or credit any overpayment to Deposit Account No. 50-0507.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO

CUSTOMER NO.: 021553

USPS EXPRESS MAIL
EL 871 050 090 US
DECEMBER 21 2001

SIGNATURE

Walter F. Fasse 12/21/01

NAME

36132

REGISTRATION NUMBER

2/p.1

SPECIFICATION

Aluminum Alloy, Aluminum Alloy Foil, Container and Method of Preparing Aluminum Alloy Foil

5

Technical Field

The present invention related to an aluminum alloy, an aluminum alloy foil and a container excellent in corrosion resistance and a method of preparing an aluminum alloy foil, and more particularly, it relates to an aluminum alloy and an aluminum alloy foil for a container for a beverage or food, a building material, a food wrapping material, a domestic article and a decorative article having high strength and sufficient elongation improving formability and exhibiting excellent rollability and a method of preparing the same.

10

15

Background Art

Among aluminum alloys, particularly those for containers for weak-acidic food containing soy sauce or sodium chloride must have sufficient corrosion resistance, strength and elongation for increasing its formability, and hence aluminum alloys such as JIS (Japanese Industrial Standard) nominal 3003, 3004 and 5052 of about 50 to 200 μm in thickness are employed in general. Table 1 shows typical compositions of these alloys.

20

Table 1

Alloy Name (JIS Nominal)	Additional Element for Aluminum Alloy (mass %)							
	Fe	Si	Cu	Mn	Mg	Cr	Zn	Ti
3003	0.7	0.6	0.1	1.2	-	-	0.10	-
3004	0.7	0.30	0.25	1.2	1.0	-	0.25	-
5052	0.40	0.25	0.10	0.10	2.5	0.20	0.10	-
1030	0.6	0.35	0.10	0.10	0.05	-	0.10	0.03
8021	1.2	0.07	0.01	-	-	-	0.10	-
8079	0.9	0.07	0.01	-	-	-	0.10	-

25

In these alloys, a corrosive phenomenon referred to as "pitting

corrosion" readily takes place in general. It is known that a surface of aluminum or an aluminum alloy is generally covered with a strong natural oxide film and hence excellent in corrosion resistance. When this oxide film is partially broken for some cause, however, corrosion takes place only in this portion and progresses in the depth direction. This phenomenon is referred to as pitting corrosion.

In order to prevent this pitting corrosion, Japanese Patent Laying-Open No. 3-261549, for example, discloses a cladding material having an aluminum film of high purity formed on its surface as a covering material. Japanese Patent Laying-Open No. 60-221546 discloses a technique of preventing pitting corrosion by adding zinc to an aluminum alloy. Further, Japanese Patent Laying-Open No. 10-183283 discloses an aluminum alloy cladding material excellent in corrosion resistance employing an aluminum alloy containing tin as a covering material.

When high-purity aluminum is employed as the covering material, however, dust is readily caused in forming due to excessive softness of the high-purity aluminum, to result in a problem of contamination.

When zinc or tin is added, the material is generally corroded although pitting corrosion can be prevented. Therefore, the quantity of corrosion is so large that the aluminum alloy is unsuitable for a container for food or the like.

Further, employment of a cladding material for a food container is generally unprofitable in consideration of the cost.

While high strength and formability are required to an aluminum alloy applied to a container for a beverage or food, those described in the aforementioned gazettes cannot sufficiently satisfy these characteristics.

High corrosion resistance and high strength are required also to an aluminum alloy foil for a building material employed as a heat insulating material, a wrapping material directed to prevention of deterioration of food or chemicals, a domestic article and a decorative article, for example, other than the container, i.e., in the field where the aluminum alloy foil is used with a thickness of not more than 50 μm . However, the aluminum alloys of the aforementioned JIS nominal 3003, 3004 and 5052 are so

remarkably work-hardened in rolling that it is difficult to roll the aluminum alloys into foils of not more than 50 μm in thickness. In particular, it is practically impossible to obtain an aluminum alloy foil of not more than 20 μm .

5 Aluminum-iron alloys such as JIS nominal 8021 and 8079 shown in Table 1 are generally employed for these thin foils. In these alloys, however, presence of aluminum-iron intermetallic compounds reduces corrosion resistance and suppresses refinement of grains for attaining sufficient strength. Therefore, these aluminum alloys are insufficient in
10 strength and never satisfactory.

Accordingly, the present invention has been proposed in order to solve the aforementioned problems, and an object of the present invention is to provide an aluminum alloy capable of preventing pitting corrosion and general corrosion without being worked into the form of a cladding material
15 and excellent in strength, formability and workability, an aluminum alloy foil consisting of this aluminum alloy and a method of preparing the same, and a container employing this aluminum alloy foil.

Disclosure of the Invention

20 In order to solve the aforementioned problems, the inventors have made various studies, to prove that copper and silicon are elements extremely reducing pitting corrosion resistance of an aluminum alloy while zinc and tin are elements causing general corrosion of the aluminum alloy under weak-acidic environment. Therefore, corrosion resistance of the
25 aluminum alloy is reduced if any of these elements is added to the aluminum alloy.

It has also been proved that manganese, iron, chromium, titanium and zirconium are elements capable of increasing the strength without damaging the corrosion resistance of the aluminum alloy and providing
30 sufficient elongation for improving the formability and high rollability for obtaining a thin foil by selecting proper contents and manufacturing conditions.

According to these recognitions, the inventors have succeeded in

developing an aluminum alloy excellent in corrosion resistance, strength, formability and rollability.

An aluminum alloy according to an aspect of the present invention, proposed according to these recognitions, contains at least 0.0001 mass % and not more than 0.03 mass % of copper, at least 0.0005 mass % and not more than 0.2 mass % of silicon, at least 0.5 mass % and not more than 4 mass % of manganese and at least 0.5 mass % and not more than 3 mass % of iron, with the rest containing aluminum and unavoidable impurities.

Preferably, the aluminum alloy contains at least 0.0001 mass % and not more than 0.03 mass % of copper, at least 0.0005 mass % and not more than 0.2 mass % of silicon, at least 1.0 mass % and not more than 3.0 % of manganese and at least 0.7 mass % and not more than 1.2 mass % of iron, with the rest containing aluminum and unavoidable impurities.

An aluminum alloy according to another aspect of the present invention further contains at least one of at least 0.01 mass % and not more than 0.5 mass % of chromium, at least 0.01 mass % and not more than 0.5 mass % of titanium and at least 0.01 mass % and not more than 0.5 mass % of zirconium in either one of the aforementioned aluminum alloys.

An aluminum alloy foil according to the present invention consists of an aluminum alloy having any of the aforementioned compositions, and has a thickness, yield strength and elongation so selected that the relation between the yield strength YS (N/mm^2) and the thickness X (μm) satisfies an inequality $YS > 28.7 \ln(X) - 30$ and the relation between the elongation El (%) and the thickness X (μm) satisfies an inequality $El > 0.15X + 3.5$.

A method of preparing the aluminum alloy foil according to the present invention having the aforementioned mechanical characteristics comprises the following steps:

(a) A step of heating up an ingot of an aluminum alloy to a temperature of at least $350^\circ C$ and not more than $580^\circ C$.

(b) A step of hot-rolling the ingot of the aluminum alloy at a starting temperature of at least $350^\circ C$ and not more than $530^\circ C$ after the heating up thereby obtaining a plate material.

(c) A step of cold-rolling the plate material after the hot rolling.

(d) A step of softening the plate material after the cold rolling.

Preferably, the aforementioned preparation method further comprises a step of holding the ingot of the aluminum alloy at a temperature of at least 350°C and not more than 580°C for not more than 15 hours after the step of heating up the ingot, and carries out the step of hot-rolling the ingot for obtaining the plate material after this holding step.

Preferably, the aforementioned preparation method carries out the step of hot-rolling the ingot for obtaining the plate material immediately after the step of heating up the ingot.

The step of softening the plate material is preferably carried out by retaining the plate material at a temperature of at least 270°C and not more than 380°C for at least one hour and not more than 20 hours.

A more preferable aluminum alloy foil according to the present invention consists of an aluminum alloy containing at least 0.0001 mass % and not more than 0.01 mass % of copper, at least 0.0005 mass % and not more than 0.1 mass % of silicon, at least 1.0 mass % and not more than 3.0 mass % of manganese and at least 0.7 mass % and not more than 1.2 mass % of iron with the rest containing aluminum and unavoidable impurities, and has a thickness, yield strength and elongation so selected that the relation between the yield strength YS (N/mm²) and the thickness X (μm) satisfies an inequality $YS > 28.7 \ln(X) - 30$ and the relation between the elongation El (%) and the thickness X (μm) satisfies an inequality $El > 0.15X + 3.5$.

A container according to the present invention consists of the aforementioned aluminum alloy foil, and has a thickness of at least 50 μm and not more than 200 μm.

The reasons why the respective elements are added, the ranges of the contents thereof, conditions for methods of preparing the same and the like are now described in detail.

(1) Copper (Cu): at least 0.0001 mass % and not more than 0.03 mass %

Copper reduces corrosion resistance of the aluminum alloy when existing in the aluminum alloy in a small quantity. Therefore, the content

of copper is set to not more than 0.03 mass %. The content of copper is set to at least 0.0001 mass % since the effect of improving pitting corrosion resistance is saturated while the cost is increased if the content of copper is set to less than 0.0001 mass %. Preferably, the content of copper is not more than 0.02 mass %, and more preferably not more than 0.01 mass %.

(2) Silicon (Si): at least 0.0005 mass % and not more than 0.2 mass %

If existing in the aluminum alloy, silicon remarkably reduces pitting corrosion resistance of the aluminum alloy against a saline solution or weak-acidic food. When the content of silicon is reduced, the grain size of the aluminum alloy is reduced. Thus, the yield strength of the aluminum alloy, i.e., the strength is increased, while the elongation of the aluminum alloy, i.e., the formability can also be improved. In order to derive these characteristics, the content of silicon must be set to at least 0.0005 mass % and not more than 0.2 mass %. The content of silicon is set to at least 0.0005 mass % since the aforementioned effect of improving the pitting corrosion resistance and the effects of increasing the formability and the strength are saturated while the cost is increased if the content of silicon is set to less than 0.0005 mass %. Preferably, the content of silicon is not more than 0.1 mass %.

(3) Manganese (Mn): at least 0.5 mass % and not more than 4 mass %

Manganese is an element improving the strength without remarkably reducing the corrosion resistance of the aluminum alloy. Sufficient strength cannot be attained if the content of manganese is less than 0.5 mass %. If the content of manganese exceeds 4 mass %, the elongation and the formability are reduced. Therefore, the content of manganese must be set to at least 0.5 mass % and not more than 4 mass %. In order to simultaneously implement corrosion resistance, strength, formability and rollability of the aluminum alloy, the content of manganese is more preferably set to at least 1.0 mass % and not more than 3.0 mass %.

When iron is added to the aluminum alloy, an intermetallic compound of aluminum-iron is formed. The presence of this intermetallic compound of aluminum-iron reduces the corrosion resistance. When

10019416.122101
manganese is added in this case, formation of the intermetallic compound of aluminum-iron reducing the corrosion resistance can be prevented. In other words, reduction of the corrosion resistance can be prevented by adding iron and manganese to the aluminum alloy thereby forming an intermetallic compound of aluminum-iron-manganese.

(4) Iron (Fe): at least 0.5 mass % and not more than 3 mass %

When the aforementioned manganese is independently added to the aluminum alloy, the softening temperature of the aluminum alloy is remarkably increased since manganese is solidly soluted in the aluminum alloy. Thus, the recrystallization temperature is also increased and the recrystallized grains are enlarged beyond necessity. If the recrystallized grains are excessively enlarged, the elongation and the yield strength of the aluminum alloy are reduced to disadvantageously reduce the formability and the strength.

When iron is added to the aluminum alloy, the quantity of solid soluted manganese in aluminum is remarkably reduced. Thus, the recrystallization temperature of the aluminum alloy is not increased beyond necessity, whereby the recrystallized grains are refined. Further, iron forms an intermetallic compound of aluminum-iron-manganese, thereby refining the recrystallized grains. More specifically, the size of the recrystallized grains reaches several μm . Thus, the elongation and the yield strength of the aluminum alloy are remarkably improved, thereby improving the formability and the strength of a molded container.

Further, addition of iron does not remarkably reduce the corrosion resistance of the aluminum alloy since manganese is added. In addition, the fine intermetallic compound of aluminum-iron-manganese having high hardness remarkably reduces seizing and formation of fine powder when forming the container, whereby the formability can be further improved.

If the content of iron is less than 0.5 mass %, the aforementioned characteristics cannot be sufficiently derived. If the content of iron exceeds 3 mass %, the intermetallic compound of aluminum-iron-manganese is rendered coarse to reduce mechanical characteristics such as the yield strength and the elongation while also reducing the rollability.

Therefore, the content of iron must be set to at least 0.5 mass % and not more than 3 mass %. In order to sufficiently derive the aforementioned characteristics, the content of iron is preferably set to at least 0.7 mass % and not more than 1.2 mass %.

5 (5) Chromium (Cr): at least 0.01 mass % and not more than 0.5 mass %

Chromium improves the strength of the aluminum alloy without remarkably reducing the corrosion resistance of the aluminum alloy. If the content of chromium is less than 0.01 mass %, the effect of improving the strength cannot be sufficiently attained. If the content of chromium exceeds 0.5 mass %, the formability is reduced. Therefore, the content of chromium must be set to at least 0.01 mass % and not more than 0.5 mass %. In order to implement excellent formability, the content of chromium is preferably set to not more than 0.25 mass %.

15 (6) Titanium (Ti): at least 0.01 mass % and not more than 0.5 mass %

Titanium improves the strength of the aluminum alloy without remarkably reducing the corrosion resistance of the aluminum alloy. Particularly when added to the aluminum alloy, titanium refines the coarse intermetallic compound of aluminum-iron-manganese causing a defect in forming. Thus, toughness can be supplied to the aluminum alloy. If the content of titanium is less than 0.01 mass %, the effects of improving the strength and supplying the toughness cannot be sufficiently attained. If the content of titanium exceed 0.5 mass %, the formability is reduced. Therefore, the content of titanium must be set to at least 0.01 mass % and not more than 0.5 mass %. In order to further derive the aforementioned effects, the content of titanium is preferably set to not more than 0.25 mass %.

25 (7) Zirconium (Zr): at least 0.01 mass % and not more than 0.5 mass %

30 While zirconium also improves the strength without remarkably reducing the corrosion resistance of the aluminum alloy, this effect is more remarkable than those of chromium and titanium. This is because addition of zirconium is extremely effective for refinement of recrystallized

grains, whereby both of improvement of the strength and assurance of the elongation can be compatibly attained while the rollability is not reduced. The aforementioned effects cannot be derived if the content of zirconium is less than 0.01 mass %, while the elongation is reduced to deteriorate the formability if the content exceeds 0.5 mass %. In order to implement excellent strength, elongation and rollability, the content of zirconium is preferably set to not more than 0.35 mass %.

According to the present invention, as hereinabove described, the aforementioned additional elements are added into aluminum in the optimum quantities, whereby the recrystallized structure of the aluminum alloy is converted to a hyperfine structure. It is the feature of the aluminum alloy according to the present invention that the strength and the formability of the aluminum alloy can be thereby simultaneously improved.

The aluminum alloy according to the present invention may contain transition elements such as vanadium (V) and nickel (Ni) and elements such as magnesium (Mg), boron (B), gallium (Ga), zinc (Zn) and bismuth (Bi) with contents not influencing the aforementioned characteristics and effects.

(8) Mechanical Characteristics of Aluminum Alloy Foil

Assuming that X (μm) represents the thickness, the relation between the yield strength YS (N/mm^2) and the thickness X (μm) satisfies the following inequality:

$$YS > 28.7 \ln(X) - 30$$

Further, the relation between the elongation El (%) and the thickness X (μm) satisfies the following inequality:

$$El > 0.15X + 3.5$$

The thickness, the yield strength and the elongation of the aluminum alloy foil are so selected as to satisfy the aforementioned two inequalities.

The strength and the elongation of the aluminum alloy foil vary with the thickness of the foil. In general, the elongation is reduced when the strength of the material is increased, while the strength is reduced when the elongation is increased. The strength and the elongation of the foil are

reduced along with reduction of the thickness thereof. On the basis of such relation, the inventors have recognized that the aluminum alloy foil can have both strength and elongation necessary for a foil for a container, a foil for a building material, a foil for a food wrapping material and foils for domestic and decorative articles when the relation between the yield strength and the thickness as well as the relation between the elongation and the thickness satisfy the aforementioned two inequalities as the mechanical characteristics of the aluminum alloy foil. In other words, excellent formability and strength cannot be maintained in application to a container or the like unless the mechanical characteristics of the aluminum alloy foil are within the ranges of the aforementioned inequalities.

The yield strength of the aluminum alloy foil according to the present invention is about 160 N/mm² at the maximum, and the elongation is about 30 %.

(9) Method of Preparing Aluminum Alloy Foil

(9-1) Homogenization Temperature for Ingot of Aluminum Alloy: at least 350°C and not more than 580°C

The homogenization temperature is set to at least 350°C and not more than 580°C, in order to finely precipitate manganese thereby suppressing grain growth in annealing and refining recrystallized grains. While homogenization may not be necessarily performed in a cast state, a problem such as a rolling crack arises in the subsequent hot rolling step in this case. Therefore, homogenization is preferably performed by heating up the ingot of the aluminum alloy to at least 350°C before the subsequent hot rolling step, so that no crack is caused in this step. When the ingot of the aluminum alloy is heated up to a temperature exceeding 580°C, precipitation density of manganese is reduced resulting in low strength. Preferably, the homogenization temperature is at least 380°C and not more than 500°C.

(9-2) Holding Time for Homogenization: at least 0 hour and not more than 15 hours

The time for holding the ingot of the aluminum alloy after heating up the same to the temperature of at least 350°C and not more than 580°C

is preferably as short as possible. Hot rolling may be performed immediately after heating up the ingot of the aluminum alloy to the aforementioned prescribed temperature, i.e., the holding time for homogenization may be set substantially to zero hour. If the holding time for homogenization exceeds 15 hours, the precipitation density of manganese is reduced resulting in low strength. Preferably, the holding time for homogenization is not more than 10 hours.

(9-3) Starting Temperature for Hot Rolling: at least 350°C and not more than 530°C

For the sake of workability of cold rolling after hot rolling and refinement of crystal grains after annealing, the hot rolling starting temperature is set to at least 350°C and not more than 530°C. A crack is caused in hot rolling although no particular problem is caused in the characteristics of the aluminum alloy if the starting temperature is lower than 350°C, and hence the starting temperature is set to at least 350°C. If the starting temperature exceeds 530°C, crystal grains are rendered coarse when hot rolling is completed, and the recrystallized grains are insufficiently refined resulting in low strength in the finally obtained aluminum alloy foil. Preferably, the hot rolling starting temperature is within the range of at least 380°C and not more than 480°C.

(9-4) Softening Conditions: at temperature of at least 270°C and not more than 380°C for at least one hour and not more than 20 hours

The aluminum alloy foil obtained by performing cold rolling after hot rolling is softened for obtaining a soft foil. If the temperature for softening is less than 270°C or the retention time is less than one hour as the condition for softening, recrystallization is so insufficiently performed that sufficient elongation cannot be attained. If the temperature for softening exceeds 380°C or the holding time exceeds 20 hours to the contrary, the recrystallized grains are rendered coarse resulting in low strength and the elongation. In order to compatibly attain desired elongation and strength, the aluminum alloy foil must be softened at a temperature of at least 270°C and not more than 380°C for at least one hour and not more than 20 hours. If steps of homogenization and hot rolling out of the aforementioned

conditions (9-1) to (9-3) are carried out before performing softening, no aluminum alloy foil having both of desired elongation and strength can be obtained even if the conditions for softening are changed.

(10) Thickness of Aluminum Alloy Foil: at least 50 μm and not more than 200 μm

If the thickness of the aluminum alloy foil is less than 50 μm , sufficient strength for serving as a container for food or the like cannot be maintained. If the thickness exceeds 200 μm , the aluminum alloy foil is hard to form. Therefore, the thickness of the aluminum alloy foil must be set to at least 50 μm and not more than 200 μm . More preferably, the thickness of the aluminum alloy foil is at least 50 μm and not more than 100 μm .

In the present invention, the content of copper and the content of silicon may be set to not more than 0.03 mass % and not more than 0.2 mass % respectively by a method of properly adding a primarily electrolyzed base metal or a high-purity aluminum base metal obtained by segregation or three-layer electrolysis to a common base metal of 99.3 mass % in purity for adjusting components, for example.

According to the present invention, as hereinabove described, it is possible to provide an aluminum alloy hardly causing both of pitting corrosion and general corrosion and capable of simultaneously improving strength and elongation. A container excellent in corrosion resistance and having high formability and strength can be provided at a low cost by working this aluminum alloy into an aluminum alloy foil as such to be applied to the container, without working the same into the form of a cladding material.

Further, the foil consisting of the aluminum alloy developed according to the present invention can exhibit sufficient effects not only for a container but also in the field of a thin foil required to be corrosion-resistant, i.e., in the field of foils for a building material serving as a heat insulating material, a wrapping material directed to prevention of deterioration of food or chemicals and domestic and decorative articles.

In addition, the composition of this aluminum alloy is not restricted

to employment in the field of foil bases or foils but exhibits sufficient effects as the composition of a thicker plate material required to be corrosion-resistant or as the composition for powder metallurgy.

5 Brief Description of the Drawings

Fig. 1 illustrates the relation between the thickness and the yield strength of aluminum alloy foils according to Example of the present invention.

10 Fig. 2 illustrates the relation between the thickness and the elongation of the aluminum alloy foils according to Example of the present invention.

Best Modes for Carrying Out the Invention

Examples of the present invention are now described.

15 (Example 1)

First, aluminum alloys (compositions Nos. 1 to 23) of various compositions were melted and cast according to an ordinary method, for preparing ingots of the aluminum alloys. The compositions Nos. 24 to 26 correspond to the compositions of JIS nominal 3003, 3004 and 5052 respectively. Table 2 shows the compositions.




Table 2

	Composition No.	Chemical Component (mass %)									Remarks
		Mn	Fe	Si	Cu	Mg	Cr	Ti	Zr	Al	
Example	1	1	0.8	0.1	<0.01	-	-	-	-	Rest	
	2	1	1	0.2	<0.01	-	-	-	-	Rest	
	3	1	1.3	0.1	<0.01	-	-	-	-	Rest	
	4	1	1	0.1	<0.01	-	0.1	-	-	Rest	
	5	1	1	0.1	<0.01	-	0.5	-	-	Rest	
	6	1	1	0.1	<0.01	-	-	0.1	-	Rest	
	7	1	1	0.1	<0.01	-	-	0.5	-	Rest	
	8	1	1	0.1	<0.01	-	0.05	0.05	-	Rest	
	9	1	1	0.1	<0.01	-	0.2	0.2	-	Rest	
	10	1	1	0.1	<0.01	-	-	-	0.05	Rest	
	11	1	1	0.1	<0.01	-	-	-	0.1	Rest	
	12	1	1	0.1	<0.01	-	-	-	0.2	Rest	
	13	1	1	0.1	<0.01	-	-	-	0.5	Rest	
	14	1	1	0.1	<0.01	-	0.1	0.1	0.1	Rest	
Comparative Example	15	4.2*	1	0.1	<0.01	-	-	-	-	Rest	
	16	0.4*	1	0.1	<0.01	-	-	-	-	Rest	
	17	1	0.4*	0.1	<0.01	-	-	-	-	Rest	
	18	1	3.2*	0.1	<0.01	-	-	-	-	Rest	
	19	1	1	0.1	0.04*	-	-	-	-	Rest	
	20	1	1	0.3*	<0.01	-	-	-	-	Rest	
	21	1	1	0.1	<0.01	-	0.7*	-	-	Rest	
	22	1	1	0.1	<0.01	-	-	0.7*	-	Rest	
	23	1	1	0.1	<0.01	-	-	-	0.7*	Rest	
	24	1	0.7	0.6	0.2	-	-	-	-	Rest	JIS3003
	25	1	0.7	0.3	0.25	1	-	-	-	Rest	JIS3004
	26	0.1	0.4	0.25	0.2	2.5	0.1	-	-	Rest	JIS5052

Marks * indicate that the components are out of the inventive ranges.

Homogenization was carried out on these ingots of the aluminum alloys having the compositions Nos. 1 to 23 at a temperature of 480°C for 5 hours, and hot rolling was started immediately after taking out the ingots from a furnace, thereby obtaining plate materials of 3 mm in thickness. Thereafter these plate materials were cold-rolled into foils of 85 μm in thickness, and annealed at a temperature of 300°C for 10 hours as softening. The ingots of the conventional aluminum alloys having the compositions Nos. 24 to 26 were processed into soft foils of 85 μm in thickness by an ordinary method.

Mechanical characteristics (yield strength and elongation) of the obtained aluminum alloy foils were measured while the aluminum alloy

foils were dipped in an aqueous solution of 50°C in temperature containing 3 mass % of sodium chloride and 25 mass % of soy sauce for observing corroded states.

- 5 1000 sheets of 30 cm in diameter were prepared from each of the aluminum alloy foils having the compositions Nos. 1 to 26. Then, the respective sheets were formed with a composite die, thereby preparing 1000 food containers. As to the respective containers, defectives were detected with a pinhole detector for calculating forming defects rates.

Table 3 shows the results of the aforementioned measurement.




Table 3

	Composition No.	Yield strength (N/mm ²)	Elongation (%)	Corrosion Resistance	Forming Defects Rate (%)
Example	1	105	26	○	0.1
	2	110	26	○	0.1
	3	115	25	○	0.15
	4	115	25	○	0.2
	5	125	20	○	0.2
	6	112	25	○	0.15
	7	118	20	○	0.2
	8	125	26	○	0.1
	9	128	24	○	0.2
	10	112	26	○	0.1
	11	118	26	○	0.1
	12	128	26	○	0.1
	13	135	20	○	0.15
	14	130	25	○	0.15
Comparative Example	15	120	10	○	4
	16	60	25	○	0.5
	17	70	20	○	0.5
	18	70	13	△	4
	19	111	25	×	0.1
	20	60	20	×	0.3
	21	145	7	△	2
	22	121	9	△	2
	23	150	12	○	0.3
	24	60	18	×	0.5
	25	80	18	×	0.5
	26	100	20	×	3

○ : not corroded.

△ : slightly corroded.

× : considerably corroded.

5

It is understood from Table 3 that the aluminum alloy foils having the compositions Nos. 1 to 14 according to the present invention are superior to the conventional aluminum alloys (compositions Nos. 24 to 26) of the JIS nominal 3003, 3004 and 5052 in all of yield strength, elongation, corrosion resistance and forming defects ratio.

10

It is also understood that the aluminum alloy foils having the compositions Nos. 1 to 14 according to the present invention are superior also to the aluminum alloy foils having the compositions Nos. 15 to 23 out

of the ranges of the present invention in total evaluation of yield strength, elongation, corrosion resistance and forming defects ratio.

(Example 2)

5 Ingots of the aluminum alloys having the compositions Nos. 1 and 11
prepared in Example 1 were worked under various preparation conditions
into foils of 85 μm in thickness, and thereafter softened within the
temperature range of 280 to 340°C. Table 4 shows preparation conditions
employed at this time, mechanical characteristics of the softened aluminum
alloy foils and forming defects rates evaluated by the method described
10 with reference to Example 1.




Table 4

	Step	Homogenization Condition		Hot Rolling	Composition No. 1			Composition No. 11		
		Temperature (°C)	Time (hr)		Yield strength (N/mm ²)	Elongation (%)	Forming Defects Rate (%)	Yield strength (N/mm ²)	Elongation (%)	Forming Defects Rate (%)
Example	A	480	5	450	105	26	0.1	118	24	0.15
	B	450	5	420	115	25	0.1	130	24	0.2
	C	420	5	400	120	25	0.15	135	23	0.2
	D	570	10	480	102	24	0.1	110	24	0.1
Comparative Example	E	340*	5	340*	rolling end crack			rolling end crack		
	F	610*	10	450	67	27	<0.1	78	26	<0.1
	G	570	20*	450	68	27	<0.1	76	26	<0.1
	H	540	5	540*	64	26	<0.1	72	25	<0.1

Marks * indicate that the preparation conditions are out of the ranges of the present invention.

It is understood from Table 4 that aluminum alloy foils prepared through steps A, B, C and D according to the present invention exhibited excellent results in yield strength, elongation and formability while aluminum alloy foils prepared through steps E, F, G and H out of the ranges of the present invention caused problems in rolling steps or had problems such as low strength.

(Example 3)

Aluminum alloy foils having different thicknesses were prepared by combining the compositions and the steps employed in Examples 1 and 2, and softened within the temperature range of 280 to 340°C. Thereafter mechanical characteristics were measured as to the respective aluminum alloy foils. Table 5 shows the results.

Table 5

	Sample No.	Composition No.	Step	Thickness (μm)	Yield strength (N/mm ²)	Elongation (%)
Example	1	1	C	85	120	25
	2	1	C	50	115	20
	3	1	C	30	110	16
	4	1	C	10	60	8
	5	1	B	50	90	21
	6	1	D	30	80	16
	7	11	C	85	135	24
	8	11	C	50	128	19
	9	11	C	30	120	16
	10	11	C	10	70	8
	11	12	A	50	140	12
	12	13	C	30	130	10
Comparative Example	13	1	F*	10	46	2*
	14	1	F*	85	67*	27
	15	15*	C	85	120	10*
	16	21*	C	85	145	7*
	17	21*	C	30	122	5*
	18	23*	C	85	150	12*

Marks * indicate that the yield strength or elongation is separated from the range of the present invention due to steps out of the inventive ranges.

It is understood from the results shown in Table 5 that aluminum alloy foils prepared in compositions and steps according to the present

invention are hardly work-hardened and hence excellent in rolling workability, can be rolled into thicknesses of about 10 μm of the so-called thin foil, and excellent in balance between yield strength and elongation in the respective thicknesses.

Fig. 1 shows the relation between the thickness and the yield strength of each sample shown in Table 5, and Fig. 2 shows the relation between the thickness and the elongation of each sample shown in Table 5. Referring to Figs. 1 and 2, marks \bigcirc denote the samples of inventive Examples, and marks \times denote samples of comparative examples. Numbers provided on the left sides of the marks \bigcirc and numbers provided on the right sides of the marks \times denote the numbers of the samples respectively. A curve shown in Fig. 1 corresponds to a curve expressed in the equation of yield strength $YS (\text{N/mm}^2) = 28.7 \ln(X) - 30$ assuming that $X (\mu\text{m})$ represents the thickness of the aluminum alloy foil, and a straight line shown in Fig. 2 corresponds to a straight line expressed in the equation of the elongation $El (\%) = 0.15X + 3.5$.

It is understood from Figs. 1 and 2 that the samples Nos. 1 to 12 of inventive Examples satisfy the inequality $YS > 28.7 \ln(X) - 30$ indicating the relation between the yield strength and the thickness and the inequality $El > 0.15X + 3.5$ indicating the relation between the elongation and the thickness, while the samples Nos. 13 to 18 of comparative examples do not satisfy either one of the aforementioned two inequalities.

It is also understood that the aluminum alloys of JIS nominal 8021 and 8079 generally employed for thin foils have yield strength and elongation of about 40 N/mm^2 and 8 % respectively at the most with a thickness of 10 μm and exhibit no corrosion resistance dissimilarly to the inventive aluminum alloy, and hence the aluminum alloy disclosed in the present invention is extremely effective also for a thin foil.

Examples disclosed this time are considered to be illustrative in all points and not restrictive. The scope of the present invention is shown not by the aforementioned Examples but the scope of claim for patent, and it is intended that all corrections and modifications within the meaning and the range equivalent to the scope of claim for patent are included.

Industrial Availability

The aluminum alloy and the aluminum alloy foil according to the present invention, having high strength and sufficient elongation
5 improving formability and exhibiting excellent rollability, can be applied to an aluminum alloy or an aluminum alloy foil for a container for beverages or food, a building material, a food wrapping material and domestic and decorative articles, while the composition of the aluminum alloy according to the present invention is not restricted to application in the field of foil or
10 foil stock but can be sufficiently applied to a thicker plate material required to be corrosion-resistant or powder metallurgy.

CLAIMS

1. An aluminum alloy containing at least 0.0001 mass % and not more than 0.03 mass % of copper, at least 0.0005 mass % and not more than 0.2 mass % of silicon, at least 0.5 mass % and not more than 4 mass % of manganese and at least 0.5 mass % and not more than 3 mass % of iron, with the rest containing aluminum and unavoidable impurities.

2. The aluminum alloy according to claim 1, containing at least 1.0 mass % and not more than 3.0 % of manganese and at least 0.7 mass % and not more than 1.2 mass % of iron.

3. The aluminum alloy according to claim 1, containing at least one element selected from a group consisting of at least 0.01 mass % and not more than 0.5 mass % of chromium, at least 0.01 mass % and not more than 0.5 mass % of titanium and at least 0.01 mass % and not more than 0.5 mass % of zirconium.

4. An aluminum alloy foil having a thickness, elongation and yield strength so selected that the relation between the yield strength YS (N/mm^2) and the thickness X (μm) satisfies an inequality $YS > 28.7 \ln(X) - 30$ and the relation between the elongation El (%) and the thickness X (μm) satisfies an inequality $El > 0.15X + 3.5$.

5. A method of preparing the aluminum alloy foil according to claim 4, comprising steps of:

heating up an ingot of an aluminum alloy to a temperature of at least 350°C and not more than 580°C ;

hot-rolling said ingot of said aluminum alloy at a starting temperature of at least 350°C and not more than 530°C after the heating up thereby obtaining a plate material;

cold-rolling said plate material after the hot rolling; and softening said plate material after the cold rolling.

10019416.122101
6. The method of preparing the aluminum alloy foil according to claim 5, further comprising a step of retaining said ingot of said aluminum alloy at a temperature of at least 350°C and not more than 580°C for not more than 15 hours after said step of heating up said ingot, and carrying out said step of hot-rolling said ingot for obtaining said plate material after said holding step.

7. The method of preparing aluminum alloy foil according to claim 5, carrying out said step of hot-rolling said ingot for obtaining said plate material immediately after said step of heating up said ingot.

8. The method of preparing the aluminum alloy foil according to claim 5, wherein said step of softening said plate material includes an operation of retaining said plate material at a temperature of at least 270°C and not more than 380°C for at least one hour and not more than 20 hours.

9. An aluminum alloy foil consisting of an aluminum alloy containing at least 0.0001 mass % and not more than 0.01 mass % of copper, at least 0.0005 mass % and not more than 0.1 mass % of silicon, at least 1.0 mass % and not more than 3.0 mass % of manganese and at least 0.7 mass % and not more than 1.2 mass % of iron with the rest containing aluminum and unavoidable impurities and having a thickness, elongation and yield strength so selected that the relation between the yield strength YS (N/mm²) and the thickness X (μm) satisfies an inequality $YS > 28.7 \ln(X) - 30$ and the relation between the elongation El (%) and the thickness X (μm) satisfies an inequality $El > 0.15X + 3.5$.

10. A container consisting of the aluminum alloy foil according to claim 9 and having a thickness of at least 50 μm and not more than 200 μm.

FIG. 1





FIG. 2



Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Declaration and Power of Attorney For Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

As a below named inventor, I hereby declare that:

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

My residence, post office address and citizenship are as stated next to my name.

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者であると（下記の名称が複数の場合）信じています。

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Aluminum Alloy, Aluminum Alloy Foil,Container and Method of PreparingAluminum Alloy Foil

上記発明の明細書（下記の欄でx印がついていない場合は、本書に添付）は、

the specification of which is attached hereto unless the following box is checked:

☐ 月 日に提出され、米国出願番号または特許協定条約国際出願番号を _____ とし、
(該当する場合) _____ に訂正されました。☒ was filed on July 3, 2000
as United States Application Number or
PCT International Application Number
PCT/JP00/04435 and was amended on
_____ (if applicable).

私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

Page 1 of 4

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner of Patents and Trademarks, Washington, DC 20231.

USPS EXPRESS MAIL
EL 871 050 090 US
DECEMBER 21 2001

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Japanese Language Declaration
(日本語宣言書)

私は、米国法典第35編119条(a)-(d)項又は365条(b)項に基づき下記の、米国以外の国の少なくとも一カ国を指定している特許協力条約365(a)項に基づき国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior Foreign Application(s)

外国での先行出願

11-195772 Pat.(Number)
(番号)Japan(Country)
(国名)

I hereby claim foreign priority under Title 35, United States Code, Section 119 (a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Priority Not Claimed

優先権主張なし

09/July/1999(Day/Month/Year Filed)
(出願年月日)☐(Number)
(番号)(Country)
(国名)(Day/Month/Year Filed)
(出願年月日)☐

私は、第35編米国法典119条(e)項に基づいて下記の米国特許出願規定に記載された権利をここに主張いたします。

(Application No.)
(出願番号)(Filing Date)
(出願日)(Application No.)
(出願番号)(Filing Date)
(出願日)

私は、下記の米国法典第35編120条に基づいて下記の米国特許出願に記載された権利、又は米国を指定している特許協力条約365条(c)に基づき権利をここに主張します。また、本出願の各請求範囲の内容が米国法典第35編112条第1項又は特許協力条約で規定された方法で先行する米国特許出願に開示されていない限り、その先行米国出願書提出日以降で本出願書の日本国内または特許協力条約国際提出日までの期間中に入手された、連邦規則法典第37編1条56項で定義された特許資格の有無に関する重要な情報について開示義務があることを認識しています。

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.

(Application No.)
(出願番号)(Filing Date)
(出願日)(Status: Patented, Pending, Abandoned)
(現況: 特許許可済、係属中、放棄済)(Application No.)
(出願番号)(Filing Date)
(出願日)(Status: Patented, Pending, Abandoned)
(現況: 特許許可済、係属中、放棄済)

私は、私自身の知識に基づいて本宣言書中で私が行なう表明が真実であり、かつ私の入手した情報と私の信じることに基づき表明が全て真実であると信じていること、さらに故意になされた虚偽の表明及びそれと同等の行為は米国法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰されること、そしてそのような故意による虚偽の声明を行なえば、出願した、又は既に許可された特許の有効性が失われることを認識し、よってここに上記のごとく宣誓を致します。

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Docket # 4296

PTO/SB/106 (8-96)
 Approved for use through 9/30/98. OMB 0651-0032
 Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Japanese Language Declaration (日本語宣言書)

委任状 我は下記の発明者として、本出願に関する一切の
 手続を米特許商標局に対して遂行する弁理士または代理人
 として、下記の者を指名いたします。(弁護士、または代理
 人の氏名及び登録番号を明記のこと)

POWER OF ATTORNEY: As a named inventor, I hereby appoint
 the following attorney(s) and/or agent(s) to prosecute this
 application and transact all business in the Patent and Trademark
 Office connected therewith (list name and registration number)

the attorneys and agents associated with U.S.P.T.O. Customer No. 21553,
 presently being Walter F. Fasse Reg No. 36132 and Wolfgang G. Fasse
 Reg. No. 21187, having a correspondence address at:
 Customer No. 21553

Fasse Patent Attorneys, P.A.
 58-G Main Road North
 P.O. Box 726
 Hampden, Maine 04444-0726
 Tel.: (207) 862-4671



021553

PATENT AND TRADEMARK OFFICE

唯一または第一発明者名

Full name of sole or first inventor

Akinori RO

発明者の署名

日付

Inventor's signature

December 14, 2001

住所

Residence

Izumi-shi, Osaka, Japan

国籍

Citizenship

Japanese

私書箱

Post Office Address

4-2-403, Ibukino 4-chome,

Izumi-shi, Osaka, Japan

第二共同発明者

Full name of second joint inventor, if any

Masaaki ABE

第二共同発明者

日付

Second inventor's signature

December 14, 2001

住所

Residence

Ikoma-gun, Nara, Japan

国籍

Citizenship

Japanese

私書箱

Post Office Address

3-17, Mimatsugaoka-nishi 1-chome,

Sangou-cho, Ikoma-gun, Nara, Japan

(第三以降の共同発明者についても同様に記載し、署名をす
 ること)

(Supply similar information and signature for third and subsequent
 joint inventors.)

USPS EXPRESS MAIL
 EL 871 050 090 US
 DECEMBER 21 2001

10039416 122101

Japanese Language Declaration

第3の共同発明者の氏名(該当する場合)	Full name of third joint inventor, if any	
	Yoshiki HASHIZUME	
同第3共同発明者の署名	日付	Third Inventor's signature Date
		Yoshiki Hashizume December 14, 2001
住所	Residence	
	Kawachinagano-shi, Osaka, Japan	
国籍	Citizenship	
	Japanese	
郵便の宛先	Post Office Address	
	413-1, Amami, Kawachinagano-shi,	
	Osaka, Japan	

第4の共同発明者の氏名(該当する場合)	Full name of fourth joint inventor, if any	
同第4共同発明者の署名	日付	Fourth Inventor's signature Date
住所	Residence	
国籍	Citizenship	
郵便の宛先	Post Office Address	

第5の共同発明者の氏名(該当する場合)	Full name of fifth joint inventor, if any	
同第5共同発明者の署名	日付	Fifth Inventor's signature Date
住所	Residence	
国籍	Citizenship	
郵便の宛先	Post Office Address	

第6の共同発明者の氏名(該当する場合)	Full name of sixth joint inventor, if any	
同第6共同発明者の署名	日付	Sixth Inventor's signature Date
住所	Residence	
国籍	Citizenship	
郵便の宛先	Post Office Address	

(第7またはそれ以降の共同発明者に対しても同様な情報および署名を提供すること。)

(Supply similar information and signature for seventh and subsequent joint inventors.)

USPS EXPRESS MAIL
EL 871 050 090 US
DECEMBER 21 2001